


## White waterproofing slurry

- for aesthetic demanding surfaces
- for concrete and masonry
- against active and passive water pressure
- applicable by mortar gun

 0761 Vandex Isoliermittel-GmbH Industriestr. 19-23 DE-21493 Schwarzenbek 09 007 EN 1504-3:2005	EN 1504-3:ZA.1a CC fine mortar for structural repair (based on hydraulic cement)	
	Compressive strength Chloride ion content Adhesive bond Carbonation resistance Modulus of elasticity Thermal compatibility Part 1: Freeze thaw with de-icing salt immersion Part 4: Dry thermal cycling Capillary absorption Reaction to fire Dangerous substances	class R3 ≥ 25 MPa ≤ 0.05% ≥ 2.0 MPa passed ≥ 20 GPa ≥ 2.0 MPa ≥ 2.0 MPa ≤ 0.5 kg/m <sup>2</sup> ·h <sup>0.5</sup> class A1 complies with 5.4

## PRODUCT DESCRIPTION

VANDEX BB WHITE is a cementitious, ready-mixed surface waterproofer.

## AREAS OF APPLICATION

- substrates: concrete and masonry
- against active and passive water pressure
- protection against water and humidity
- walls, etc.
- drinking water structures

## PROPERTIES

Owing to its composition of cement, quartz with graded grain-size distribution and selected additives, VANDEX BB WHITE is waterproof. It can be employed against active and passive water pressures. The initial bonding capability of VANDEX BB WHITE is excellent, making it suitable to be applied to horizontal as well as vertical surfaces. It is durable, resistant to frost and heat after setting, and at the same time vapour permeable. VANDEX BB WHITE is tested for use in contact with drinking water.

## SURFACE PREPARATION

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance must be removed by suitable means.

Water leaks must be stopped e.g. with the VANDEX PLUG. Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

### Brick- and blockwork substrates

Any remaining plaster, render or other substances that could inhibit bonding must be removed back to the substrate. Gypsum, remains of wood or other foreign material must be removed by appropriate means. Loose pointing must be routed out and the substrate cleaned thoroughly.

## MIXING

Mix 25 kg of VANDEX BB WHITE with 5–6.25 litres of tap water in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a mechanical mixer.

## APPLICATION

VANDEX BB WHITE is applied with brush, trowel or suitable spray equipment.

A maximum of 2 mm (approx. 4 kg/m<sup>2</sup>) can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to relevant specification.

It is recommended to apply the next coat whilst the previous coat is still damp on the surface. The previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat must be textured by suitable means whilst still plastic to form a key.

To maintain workability of the material do not add water, simply re-stir the mixture.

### Brush application

Ensure that all cavities in the substrate are filled.

### Trowel application

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

### Spray application

VANDEX BB WHITE can be applied with a suitable fine mortar spraying device.

For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6 mm.

The first layer of Vandex is applied in a circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

Do not apply at temperatures below +5 °C, or to a frozen substrate.

## CONSUMPTION

Type of water impact	Recommended overall application rate	Total layer thickness (approx.)
Pressureless water	4 kg/m <sup>2</sup>	2 mm
Water under pressure	6 kg/m <sup>2</sup>	3 mm

### Note:

Substrate and application conditions have to be observed. Depending on surface roughness, consumption may vary.

## CURING

Keep damp for at least 5 days and provide suitable protection against extreme weather conditions (e.g. sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 h.

## PACKAGING

25 kg PE-lined paper bag

## STORAGE

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

## HEALTH AND SAFETY

VANDEX BB WHITE contains cement. – Irritating to respiratory system and skin. Risk of serious damage to eyes. – Keep out of the reach of children. Do not breathe dust. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Wear suitable gloves and eye/face protection. If swallowed, seek medical advice immediately and show this container or label. – For further information please refer to Safety Data Sheet on [www.vandex.com](http://www.vandex.com).

TECHNICAL DATA		
Appearance		white powder
Density of wet mix	[kg/l]	approx. 2.0
Workability at 20 °C	[min]	approx. 45
Setting time at 20 °C	[h]	approx. 3–5
Compressive strength 28 d	[MPa]	approx. 35
Bending tensile strength 28 d	[MPa]	approx. 6
Static modulus of elasticity 28 d	[GPa]	approx. 22
Capillary absorption	[kg/m <sup>2</sup> ·h <sup>0.5</sup> ]	0.08
Further data		refer to CE marking
All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.		

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



An **RPM** Company

### HEAD OFFICE AND INTERNATIONAL SALES:

**Vandex International Ltd**

P.O. Box · CH-4501 Solothurn/Switzerland

+41 32 626 36 36 · [info@vandex.com](mailto:info@vandex.com) · [www.vandex.com](http://www.vandex.com)

### PRODUCTION:

**Vandex Isoliermittel-Gesellschaft m.b.H.**

P.O. Box · D-21487 Schwarzenbek/Germany

